



METALWORKING PRODUCT SUMMARY

TEST	CUT 201	CUT 300	CUT 355	CUT 400	CUT 462	CUT 462 NC	CUT 4575	GDO	HONNG	DRAWING
Viscosity @ 40 °C	NA	NA	NA	23.8	25.7	31.0	30.8	13.9	4.1	37.00
API Gravity, 60 °F	28	31.2	31.2	31.0	29.2	29.2	31.6	30.6	32.5	28.0
Flash Point, PM, °F	330	345	345	345	345	345	345	240	260	360
Fat, %	1.0	-	7.5	5.1	8.0	10.0	-	10.0	3.0	27.5
Total Sulfur, %	-	1.8	0.8	1.2	1.6	1.6	0.2	3.2	-	-
Active Sulfur, %	-	1.7	-	1.0	.06	1.0	-	2.6	-	-
Chlorine, %	2.0	-	0.5	--	1.0	-	-	2.3	-	-
Phosphorous. %	-	-	-		-	0.3	0.12	-	-	-
Color, ASTM	<2.0	<7.5	<7.5	<7.5	<7.5	<7.5	<2.0	<7.5	<2.0	<3.0

0807