Advanced Lubrication Specialties 420 Imperial Court Bensalem, PA 19020 United States

Tel: (215) 244-2114 Fax: (215) 244-2118 www.advancedlubes.com



ADVANTAGE PAO SYNTHETIC LUBRICANTS

OVERVIEW

ADVANTAGE PAO SYNTHETIC LUBRICANTS are synthetic gearbox, bearing, and circulating oils that are formulated from premium polyalphaolefin (PAO) base fluids for enclosed systems requiring ashless antioxidants and anti-wear. These oils have been designed to provide proper lubrication under hydrodynamic and mild boundary lubrication conditions. They are recommended for gear systems where moderate loads and high temperatures are expected, including worm gears containing soft metals such as bronze, brass and copper.

FEATURES & BENEFITS

ADVANTAGE PAO SYNTHETIC LUBRICANTS are 100% synthetic PAO lubricants formulated for wide operating temperature ranges. Their low pour points and high flash points provide increased thermal and oxidative stability over mineral based lubricants.

APPLICATIONS

ADVANTAGE PAO SYNTHETIC LUBRICANTS are designed to be multipurpose lubricants that can be used a wide variety of industrial applications. They are similar to petroleum oils in their compatibility to seals, hoses, gaskets and paint. Key applications include: rotary screw compressors, rotary vane compressors, centrifugal compressors, reciprocating compressors, vacuum pumps, hydraulic systems, blowers, enclosed spur, helical, bevel & worm gear units, plain and roller contact bearings, circulating and splash lubricated systems, and mist systems.

TYPICAL PROPERTIES										
Product Code	964	965	966	967	968	969	980	981	727	TBD
ISO Viscosity Grade	32	46	68	100	150	220	320	460	680	1000
Viscosity, cSt @ 40 °C	31.1	47.3	68.6	95.2	156.3	230.4	311.3	486.2	676.7	980.9
Viscosity, cSt @ 100 °C	5.75	7.86	10.1	12.85	18.29	24.14	29.57	41.37	54.35	98.02
Viscosity Index	127	136	132	133	131	131	130	133	133	136
Flash Point, °C	240	240	238	260	260	262	270	270	270	270
Pour Point, °C	-48	-48	-48	-45	-35	-33	-27	-25	-25	-23
Copper Corrosion	1B	1B	1B	1B	1B	1B	1B	1B	1B	1B
Rust Prevention	Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass
Evaporation, %	<1%	<1%	<1%	<1%	<1%	<1%	<1%	<1%	<1%	<1%
Specific Gravity	0.86	0.86	0.87	0.87	0.87	0.87	0.88	0.88	0.88	0.88